

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
8 January 2004 (08.01.2004)

PCT

(10) International Publication Number
WO 2004/003269 A1

(51) International Patent Classification⁷:
D01F 6/74, C08J 5/18 // C08L 79:04

D01D 10/02,

(74) Agent: HEIMANN, Annette; CPW GMBH, Kasinos-
trasse 19-21, 42103 Wuppertal (DE).

(21) International Application Number:

PCT/EP2003/006578

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,
SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 23 June 2003 (23.06.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:
02014303.8

27 June 2002 (27.06.2002) EP

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): TELJIN
TWARON B.V. [NL/NL]; Westervoortsedijk 73, NL-6827
AV Arnhem (NL).

Published:

— with international search report

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): ZEGERS, Hendrikus,
Cornelis [NL/NL]; Vleugelstraat 13, NL-6922 JM Duiven
(NL).

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR OBTAINING A SYNTHETIC ORGANIC AROMATIC HETEROCYCLIC ROD FIBER OR FILM
WITH HIGH TENSILE STRENGTH AND/OR MODULUS

(57) **Abstract:** The invention pertains to a process for obtaining a synthetic organic aromatic heterocyclic rod fiber or film with high
tensile strength and/or modulus comprising spinning a synthetic organic polymer to a aromatic heterocyclic rod fiber or obtaining the
synthetic organic polymer as an aromatic heterocyclic rod film, followed by loading the fiber or film in the presence of a processing
aid, at a temperature below the boiling point of the processing aid and above -50°- C, at a tension of 10 to 95 % of the fiber or film
breaking strength, followed by removing the processing aid and/or performing a heating step at a tension of 10 to 95% of the fiber
or film breaking strength.

WO 2004/003269 A1